Axiall PVC 8491

Semi-Rigid Polyvinyl Chloride

Axiall Corporation

Message:

Clear, semi-rigid extrusion grade compound formulated for good UV stability.

General Information			
Features	Good UV Resistance		
	High Clarity		
	Semi Rigid		
Appearance	Clear/Transparent		
Processing Method	Extrusion		
Hardness	Nominal Value		Test Method
Durometer Hardness			ASTM D2240
Shore D	53 to 59		
Shore D ¹	46 to 52		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	20.7	MPa	ASTM D638
Tensile Elongation (Break)	280	%	ASTM D638
Extrusion	Nominal Value	Unit	
Melt Temperature	191	°C	
NOTE			
1.	Delayed		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

