

Vital-Line SHE8595G

Flexible Polyvinyl Chloride

Teknor Apex Asia Pacific PTE. LTD.

Message:

Vital-Line SHE8595G is a flexible polyvinyl chloride material. This product is available in the Asia-Pacific region and is processed by extrusion.

The main features of Vital-Line SHE8595G are:

sterilizable

Good flexibility

plasticization

The typical application fields of Vital-Line SHE8595G are: medical/health care

General Information			
Features	Non-phthalate plasticizer		
	Radiation disinfection		
	Good flexibility		
Uses	Medical/nursing supplies		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.16 - 1.20	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	60 - 66		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	> 11.8	MPa	ASTM D638
Tensile Elongation (Break)	> 200	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Thermal stability-Oven (190°C)	> 30.0	min	ASTM D2115-92
Additional Information			
Typical temperature profile for processing compound is from 135°C to 180°C. The optimum temperatures depend on the type of machine as well as screw design being used to process. Feeding zone: 135°C Compression zone: 145°C~155°C Mixing zone: 155°C~175°C Nozzle/Die Zone: 160°C~180°C			
NOTE			

1. 500 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

