

# Spartech Polycom A32299

High Impact Polystyrene

Spartech Polycom

Message:

Talc / Calcium Stearate Polystyrene Compound

General Information			
Filler / Reinforcement	Talc filler, 20% filler by weight		
Additive	Calcium stearate (10%)		
Forms	Particles		
	Particle		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.0	g/10 min	ASTM D1238

Injection	Nominal Value	Unit
Processing (Melt) Temp	135 - 321	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

