

SABIC® LLDPE 6335BE

Linear Low Density Polyethylene

Saudi Basic Industries Corporation (SABIC)

Message:

SABIC® LLDPE 6335BE is a hexene linear low density polyethylene resin for cast film applications. The product has been specially formulated for optimum thermal stability at high temperatures used in cast film extrusion. Cast films produced from SABIC® LLDPE 6335BE exhibit excellent optical properties, toughness, puncture resistance, tear strength and stiffness. The suffix E denotes European origin.

Application

SABIC® LLDPE 6335BE resin is recommended for use in non cling layers in pallet stretch wrap (pre-stretch), high performance draw down films and other mono layer and coextruded film applications where high strength is required.

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/medical applications.

General Information			
Additive	Antioxidation		
Features	Low density		
	Rigid, good		
	Optical		
	hexene comonomer		
	Perforation resistance		
	Antioxidation		
	Good tear strength		
	Thermal stability, good		
	Good toughness		
Uses	Stretch winding		
	cast film		
Processing Method	cast film		
Physical	Nominal Value	Unit	Test Method
Density	0.935	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.8	g/10 min	ISO 1133
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	20	µm	
Elastic Recovery - Cast Film (20.0 µm)	46	%	ASTM D5459
Protrusion Puncture Resistance - Cast Film (20.0 µm)	1.40	J	ASTM D5748
Stress Retention - Cast Film (20.0 µm)	75	%	ASTM D5459
Dart Impact - Cast Film (20.0 µm)	14.0	J/cm	ISO 7765-2
Tear Strength - TD ¹ (20.0 µm)	227.0	kN/m	ISO 6383-2
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	117	°C	ISO 306/A
Melting Temperature (DSC)	126	°C	Internal method

Optical	Nominal Value	Unit	Test Method
Gloss (45°, 20.0 µm, Cast Film)	87		ASTM D2457
Haze (20.0 µm, Cast Film)	3.1	%	ASTM D1003A
Additional Information	Nominal Value	Unit	Test Method
Properties are determined on 20 µm cast stretch film produced on a 2 m commercial cast stretch film line: melt temperature 270°C, chill roll temperature 20°C and line speed 450 m/min.			
Extrusion	Nominal Value	Unit	
Melt Temperature	250 - 300	°C	
NOTE			
1.	Cast Film		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

