

MALECCA K-096

Acrylonitrile Butadiene Styrene

Denka Company Limited

Message:

MALECCA K-096 is an Acrylonitrile Butadiene Styrene (ABS) product. It can be processed by injection molding and is available in Asia Pacific, Europe, or North America. Primary characteristic: flame rated.

General Information			
UL YellowCard	E49895-100680002		
UL File Number	E49895		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.05	g/cm ³	ASTM D792
23°C	1.06	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	10	g/10 min	ISO 1133
Molding Shrinkage (2.00 mm)	0.40 to 0.60	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
R-Scale	114		ASTM D785
R-Scale	113		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	42.0	MPa	ASTM D638
--	2500	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield	48.0	MPa	
Break	38.0	MPa	
Nominal Tensile Strain at Break	29	%	ISO 527-2/50
Flexural Modulus			
-- ²	2350	MPa	ASTM D790
-- ³	2450	MPa	ISO 178
Flexural Strength			
-- ⁴	74.0	MPa	ASTM D790
-- ⁵	76.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	21	kJ/m ²	ISO 179
Notched Izod Impact	210	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			

1.8 MPa, Unannealed ⁶	100	°C	ASTM D648
1.8 MPa, Unannealed	90.0	°C	ISO 75-2/Af
Vicat Softening Temperature	110	°C	ISO 306/B, ASTM D1525 ⁷
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	
Drying Time	3.0 to 4.0	hr	
Rear Temperature	200 to 220	°C	
Middle Temperature	210 to 240	°C	
Front Temperature	220 to 250	°C	
Nozzle Temperature	220 to 245	°C	
Mold Temperature	50.0 to 80.0	°C	
Back Pressure	0.490 to 0.981	MPa	
Screw Speed	50 to 80	rpm	
NOTE			
1.	5.0 mm/min		
2.	15 mm/min		
3.	2.0 mm/min		
4.	15 mm/min		
5.	2.0 mm/min		
6.	Edgewise		
7.	Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

