

Miflon® 3313

Polytetrafluoroethylene

Jiangsu Meilan Chemical Co., Ltd.

Message:

Suspension PTFE Resin (Virgin Granular) (PTFE)

Quality Standard: Q/321200GDH014-2012

Reference Standard: HG/T2902-1997

Cleanness

Not clean and well-distribution, or have small metal impurities, more than 2 impurities (=1mm)

General Information		
Forms	Granules	
Physical	Nominal Value	Unit
Moisture Content	< 0.050	%
Mechanical	Nominal Value	Unit
Tensile Strength	> 16.0	MPa
Tensile Elongation (Break)	> 200	%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

