## **Chemical Resources BPP1200**

Polypropylene Impact Copolymer

Chemical Resources, Inc.

## Message:

BPP1200 is formulated for Injection Molding.

It meets the requirements of the FDA regulation 21CFR.1520

General Information				
Features	Food Contact Acceptable			
	Impact Copolymer			
Agency Ratings	FDA 21 CFR 177.1520	FDA 21 CFR 177.1520		
Processing Method	Injection Molding	Injection Molding		
Physical	Nominal Value	Unit	Test Method	
Melt Mass-Flow Rate (MFR) (230°C/2.10	6			
kg)	12	g/10 min	ASTM D1238	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Yield)	24.1	MPa	ASTM D638	
Tensile Elongation (Yield)	8.0	%	ASTM D638	
Flexural Modulus	1380	MPa	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact (23°C)	190	J/m	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load (0. MPa, Unannealed)	.45 98.9	°C	ASTM D648	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

