

Borclean™ HC314BF

Polypropylene Homopolymer

Borealis AG

Message:

Borclean HC314BF is a polypropylene homopolymer.

Borclean HC314BF contains no slip, antiblock, antistatic additives or nucleating additives.

General Information			
Features	Additive Free		
	Good Processability		
	Good Stiffness		
	High Purity		
	Homopolymer		
	Metallizable		
	Non-Smooth Surface Finish		
	Recyclable Material		
Uses	Bi-axially Oriented Film		
	Electrical/Electronic Applications		
	Film		
Forms	Pellets		
Processing Method	Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.9	g/10 min	ISO 1133
Ash Content	10 to 20	ppm	ISO 3451-1
Calcium ¹	5	ppm	Internal Method
Catalyst Residue			Internal Method
Aluminium (ICP)	2 to 4	ppm	
Chloride (XRF)	1 to 3	ppm	
Titanium (ICP)	1 to 3	ppm	
Isotactic Index ²	96	%	Internal Method
Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC)	161 to 165	°C	ISO 3146
Electrical	Nominal Value		Test Method
Dielectric Constant	2.25		IEC 60250
NOTE			
1.	from anti-acid		
2.	Decaline soluble		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

