# Boda BDF-KK2801

#### Fluoroelastomer

Chenguang Fluoro & Silicone Elastomers Co., Ltd.

## Message:

Material Type: Brown color fluoroelastomer compound, hardness Shore A 75-85.

Based on bisphenol curable copolymers.

Features: Good mold flow, improved mold release, low compression set.

Process Methods: Suitable for compression, injection and transfer molding processes.

Good Flow

Good Mold Release

Applications: O-rings, gaskets and other sealing parts.

Lab Testing Curing Condition: Press Curing: 10min@170°C. Oven: (8+16)hrs@230°C

General Information

Features

	Good Mold Release			
	Good Moldability			
	Low Compression Set			
Uses	Gaskets			
	Seals			
Appearance	Brown			
Processing Method	Compression Molding			
	Injection Molding			
	Resin Transfer Molding			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.92	g/cm³	ASTM D792	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A)	81		ASTM D2240	
Elastomers	Nominal Value	Unit	Test Method	
Tensile Strength (Yield)	14.0	MPa	ASTM D412	
Tensile Elongation (Break)	190	%	ASTM D412	
Compression Set <sup>1</sup> (200°C, 70 hr)	20	%	ASTM D395	
Aging	Nominal Value	Unit	Test Method	
Change in Tensile Strength in Air (250°C,				
70 hr)	-4.0	%	ASTM D573	
Change in Ultimate Elongation in Air (250°C, 70 hr)	-40	%	ASTM D573	
Change in Durometer Hardness in Air (250°C, 70 hr)	2.0		ASTM D573	
Change in Tensile Strength (23°C, 70 hr, in Reference Fuel C)	-13	%	ASTM D471	

Change in Ultimate Elongation (23)	°C, 70		
hr, in Reference Fuel C)	-17	%	ASTM D471
Change in Durometer Hardness (23	3°C, 70		
hr, in Reference Fuel C)	-3.0		ASTM D471
Change in Volume (23°C, 70 hr, in			
Reference Fuel C)	4.0	%	ASTM D471
NOTE			
1.	6 mm Buttons		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

