

Hostacom BJ23A

Polypropylene Copolymer
LyondellBasell Industries

Message:

Hostacom BJ23A medium melt flow, 5,500 MPa flexural modulus, chemically coupled, 30% glass fiber-reinforced polypropylene copolymer has excellent impact strength, high stiffness, and very good processability. It was designed primarily for automotive instrument panel support components and various appliance parts.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Chemically Coupled		
	Copolymer		
	Good Impact Resistance		
	Good Moldability		
	High Rigidity		
Uses	Medium Flow		
	Automotive Applications		
	Automotive Under the Hood		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	11	g/10 min	ASTM D1238, ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	71.0	MPa	ISO 527-2
Tensile Strain (Yield)	6.0	%	ISO 527-2
Flexural Modulus	5500	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180
-40°C	8.3	kJ/m ²	
23°C	12	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	144	°C	ISO 75-2/A
CLTE - Flow (-30 to 100°C)	3.5E-5	cm/cm/°C	ASTM E228, ISO 11359-2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT