

Multilon® TN-7295

Polycarbonate + ABS

TEIJIN LIMITED

Message:

PC/ABS polymer alloy, Non-halogen type flame resistant series

General Information			
UL YellowCard	E98529-101053700		
Additive	Flame retardancy		
Features	Heat resistance, high		
	Halogen-free		
	Bromine-free		
	Flame retardancy		
Uses	Electrical housing		
	Business equipment		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Molding Shrinkage			Internal method
Transverse flow: 4.00mm	0.60 - 0.80	%	Internal method
Flow: 4.00mm	0.60 - 0.80	%	Internal method
Water Absorption (23°C, 24 hr)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2600	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield	70.0	MPa	ISO 527-2/50
Fracture	60.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	3.0	%	ISO 527-2/50
Fracture	90	%	ISO 527-2/50
Flexural Modulus ¹	2600	MPa	ISO 178
Flexural Stress ²	100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	14	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			

0.45 MPa, not annealed	110	°C	ISO 75-2/B
1.8 MPa, not annealed	100	°C	ISO 75-2/A
Vicat Softening Temperature	112	°C	ISO 306/B50
Linear thermal expansion coefficient			ISO 11359-2
Flow	8.0E-5	cm/cm/°C	ISO 11359-2
Lateral	8.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.70 mm	V-2		UL 94
1.0 mm	V-1		UL 94
1.5 mm	V-0		UL 94
2.0 mm	5VB		UL 94
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

