Hanwha Total PP HTH52

Polypropylene

HANWHA TOTAL PETROCHEMICALS Co., Ltd.

Message:

HTH52 is a high crystalline polypropylene that provides superior mechanical properties, including flexural modulus, surface hardness and tensile strength. Their use will also result in reduced product weight.

| General Information | | | | |
|---------------------------------------|---------------------------|----------|-------------|--|
| Additive | Antistatic | | | |
| Features | Antistatic | | | |
| | Crystalline | | | |
| | Good Processability | | | |
| | Good Weather Resistance | | | |
| | High Heat Resistance | | | |
| | High Stiffness | | | |
| | High Tensile Strength | | | |
| | Medium Hardness | | | |
| | Scratch Resistant | | | |
| | | | | |
| Uses | Automotive Interior Parts | | | |
| Forms | Pellets | | | |
| Processing Method | Injection Molding | | | |
| Physical | Nominal Value | Unit | Test Method | |
| Density | 1.04 | g/cm³ | ASTM D1505 | |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 | 45 | 40 · | ACTNA D1220 | |
| kg) | 15 | g/10 min | ASTM D055 | |
| Molding Shrinkage - Flow | 1.4 | % | ASTM D955 | |
| Hardness | Nominal Value | Unit | Test Method | |
| Rockwell Hardness (R-Scale) | 106 | 11.2 | ASTM D785 | |
| Mechanical | Nominal Value | Unit | Test Method | |
| Tensile Strength | 27.2 | N/D | ASTM D638 | |
| Yield | 37.3 | MPa | | |
| Break | 35.3 | MPa | ACTA DCOO | |
| Tensile Elongation (Break) | 15 | % | ASTM D638 | |
| Flexural Modulus | 3530 | MPa | ASTM D790 | |
| Impact | Nominal Value | Unit | Test Method | |
| Notched Izod Impact | 27 | | ASTM D256 | |
| -30°C | 27 | J/m | | |
| 23°C | 34 | J/m | | |
| Thermal | Nominal Value | Unit | Test Method | |

| Deflection Temperature Under Load (0.45 | |
|---|--|
| MPa. Unannealed) | |

°C

ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

143

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

