

Generic PP+EPDM - Talc

Polypropylene + EPDM Rubber

Generic

Message:

This data represents typical values that have been calculated from all products classified as: Generic PP+EPDM - Talc
This information is provided for comparative purposes only.

General Information			
Filler / Reinforcement	Talc filler		
Physical	Nominal Value	Unit	Test Method
Molding Shrinkage (23°C)	1.1 - 2.7	%	ISO 294-4
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 90.0	°C	
Drying Time	3.0 - 4.0	hr	
Processing (Melt) Temp	225 - 240	°C	
Mold Temperature	44.8 - 45.0	°C	
Injection Pressure	95.0 - 100	MPa	
Injection instructions			

This data represents typical values that have been calculated from all products classified as: Generic PP+EPDM - TalcThis information is provided for comparative purposes only.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

