

# MarFlex® 7235B

Linear Low Density Polyethylene

Chevron Phillips Chemical Company LLC

## Message:

MarFlex® 7235B is a Linear Low Density Polyethylene material. It is available in Latin America or North America for cast film or coextrusion.

Important attributes of MarFlex® 7235B are:

Good Aesthetics

Good Processability

Hexene Comonomer

Slip

Typical applications include:

Additive/Masterbatch

Film

Food Contact Applications

Packaging

General Information			
Additive	High Slip		
Features	Good Drawdown		
	Good Processability		
	Hexene Comonomer		
	High Slip		
	Opticals		
Uses	Blending		
	Film		
	Food Wrap		
	Packaging		
Forms	Pellets		
Processing Method	Cast Film		
	Coextrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.923	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.5	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction (Cast Film)	0.10		ASTM D1894
Films	Nominal Value	Unit	Test Method
Secant Modulus			ASTM D882
1% Secant, MD : 32 µm, Cast Film	214	MPa	
1% Secant, TD : 32 µm, Cast Film	228	MPa	
Tensile Strength			ASTM D882

MD : Break, 32 μm,Cast Film	34.0	MPa	
TD : Break, 32 μm,Cast Film	22.0	MPa	
Tensile Elongation			ASTM D882
MD : Break, 32 μm,Cast Film	500	%	
TD : Break, 32 μm,Cast Film	700	%	
Dart Drop Test - Cast Film (31.8 μm)	27.0	kN/m	ASTM D1709
Elmendorf Tear Strength <sup>1</sup>			ASTM D1922
MD : 31.8 μm	57.9	kN/m	
TD : 31.8 μm	173.7	kN/m	
Optical	Nominal Value	Unit	Test Method
Gloss (60°, 31.8 μm, Cast Film)	140		ASTM D2457
Haze (31.8 μm, Cast Film)	4.0	%	ASTM D1003
NOTE			

1. Cast Film

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

