

Wanthane® WHT-1195B

Thermoplastic Polyurethane Elastomer (Polyester)

Wanhua Chemical Group Co., Ltd.

Message:

TYPE: Polyester-based grade Extrusion grade
FEATURES: Excellent mechanical properties, high abrasion resistance, wear resistance.
Applications: Wire & Cable, tubes, conveyor belts, etc.

General Information			
Features	Good wear resistance		
	Good wear resistance		
Uses	Conveyor		
	Wire and cable applications		
	Pipe fittings		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A	95		ASTM D2240
Shaw D	50		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
DIN Abrasion	42.0	mm ³	ISO 4649
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% strain	12.0	MPa	ASTM D412
300% strain	26.0	MPa	ASTM D412
Tensile Strength (Break)	48.0	MPa	ASTM D412
Tensile Elongation (Break)	420	%	ASTM D412
Tear Strength	130	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-33.0	°C	ASTM D3418
Vicat Softening Temperature	125	°C	ASTM D1525
Injection	Nominal Value	Unit	
Drying Temperature	100 - 110	°C	
Drying Time	2.0 - 3.0	hr	

Suggested Max Moisture	0.030	%
Screw L/D Ratio	25.0:1.0 to 30.0:1.0	
Screw Compression Ratio	2.0 : 1.0 - 3.0 : 1.0	
Extrusion	Nominal Value	Unit
Drying Temperature	100 - 110	°C
Drying Time	2.0 - 3.0	hr
Suggested Max Moisture	0.030	%
Cylinder Zone 1 Temp.	190	°C
Cylinder Zone 2 Temp.	195	°C
Cylinder Zone 3 Temp.	200	°C
Cylinder Zone 4 Temp.	205	°C
Adapter Temperature	210	°C
Die Temperature	200 - 205	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

