

Thermoset Plastics 300 No.67

Epoxy; Epoxide

Thermoset, Lord Chemical Products

Message:

Thermoset Plastics 300 No.67 is an Epoxy; Epoxide (Epoxy) material. It is available in North America for casting or encapsulating.

Important attributes of Thermoset Plastics 300 No.67 are:

Heat Resistant

Insulating

Typical application of Thermoset Plastics 300 No.67: Wire & Cable

General Information			
Features	Electrically Insulating		
	Good Thermal Stability		
Uses	Electronic Insulation		
Appearance	Black		
Forms	Pellets		
Processing Method	Casting		
	Encapsulating		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.49	g/cm ³	ASTM D792
Water Absorption (24 hr)	0.15	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	96		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	59.3	MPa	ASTM D638
Tensile Elongation (Yield)	4.0	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	17	J/m	ASTM D256
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	3.0E+16	ohms · cm	ASTM D257
Dielectric Constant (1 MHz)	4.50		ASTM D150
Dissipation Factor (1 MHz)	0.040		ASTM D150
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
Hardener	Mix Ratio by Weight: 12		
Resin	Mix Ratio by Weight: 100		
Thermoset Mix Viscosity (25°C)	8000	cP	ASTM D2393
Demold Time (100°C)	120	min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

