Unichem 9003C

Flexible Polyvinyl Chloride

Colorite Polymers

Message:

Unichem 9003C is a clear non-cadmium containing vinyl extrusion compound designed to meet the requirements of General Motors material specification GMP PVC 010.

| General Information | | | | |
|---|-------------------------------------|---------------------------|-------------|--|
| Features | Antibacterial property | | | |
| | Good processing stability | | | |
| | Good weather resistance | | | |
| | Definition, high | | | |
| | | | | |
| Uses | Application in Automobile Field | | | |
| | Automotive exterior parts | | | |
| | Car exterior decoration | | | |
| Appearance | Available colors | | | |
| | Clear/transparent | | | |
| Forms | Particle | | | |
| Processing Method | Extrusion | | | |
| - | | | | |
| Physical | Nominal Value | Unit | Test Method | |
| Specific Gravity | 1.26 | g/cm³ | ASTM D792 | |
| Hardness | Nominal Value | Unit | Test Method | |
| Durometer Hardness (Shore D, 15 sec) | 38 | | ASTM D2240 | |
| Mechanical | Nominal Value | Unit | Test Method | |
| Tensile Strength ¹ (Yield) | 22.5 | MPa | ASTM D638 | |
| Tensile Elongation ² (Break) | 330 | % | ASTM D638 | |
| Additional Information | | | | |
| Volatile Loss, ASTM D1203, Method A, 10 Resistance, GM 9329P: PassesPink Stain, G 2500 kj/m: E=1.56Direct Exposure Weathe | M 9303P: PassesMixed Fungal Resista | ince, GM 9328P: PassesAcc | | |

| NOTE | |
|------|------------------|
| 1. | Type 4,500mm/min |
| 2. | Type 4,500mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

