

# TEKNIFLEX® MED 2001-0200

PP Film

Tekni-Films, a div of Tekni-Plex

Message:

100% PP Flexible Film for Medical Fluids

Tekniflex® MED 2001-0200 is an unconventionally extruded flexible polypropylene film that has excellent clarity compared to conventional tubular PP films. The film shows little or no shrink, up to 140°C (284°F) in MD and TD. The film is suitable for steam sterilisation at 121°C, is puncture and tear resistant, heat sealable and has high moisture barrier properties. This film is plasticizer, halogen and elastomer free and offers a cost efficient alternative to high end multi-layer film structures.

General Information		
Features	Food Contact Acceptable	
	Good Flexibility	
	Good Tear Strength	
	Halogen Free	
	Heat Sealable	
	High Clarity	
	Low Shrinkage	
	Moisture Barrier	
	Puncture Resistant	
	Steam Sterilizable	
Uses	Medical/Healthcare Applications	
Agency Ratings	EP Monograph 3.1.3	
	EP Monograph 3.1.6	
	EP Monograph 3.2.2	
	EU Food Contact, Unspecified Rating	
	FDA 21 CFR 177.1520	
Appearance	Clear/Transparent	
	Film	
Physical	Nominal Value	Unit
Specific Gravity	0.890	g/cm <sup>3</sup>
Films	Nominal Value	Unit
Film Thickness <sup>1</sup>	200	µm
Yield	5.53	m <sup>2</sup> /kg
Roll Width <sup>2</sup>	< 125.00	cm
Tensile Elongation - MD (Break)	600	%
Seal Initiation Temperature	140 to 150	°C
Oxygen Transmission Rate (23°C, 100% RH)	1000	cm <sup>3</sup> /m <sup>2</sup> /24 hr

Water Vapor Transmission Rate (38°C, 90% RH)	2.0	g/m <sup>2</sup> /24 hr
Optical	Nominal Value	Unit
Haze	3.0 to 5.0	%
NOTE		
1.	Thickness tolerance: ±5%	
2.	Roll width tolerance: ±1.5 mm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT