# Edgetek™ NN-35MG/000 Black v1.1

### Polyamide 66

### PolyOne Corporation

#### Message:

The Edgetek® Engineering Thermoplastic Compounds portfolio covers a broad range of standard and custom-formulated high performance materials. This portfolio includes high-temperature materials for elevated service temperature environments, high-modulus / structural materials for load-bearing and high-strength applications and flame-retardant products. These compounds are based on select engineering thermoplastic resins that are compounded with reinforcing additives such as carbon fiber, glass fiber and glass beads.

General Information			
Filler / Reinforcement	Mineral,35% Filler by Weight		
Uses	Automotive Applications		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.52	g/cm³	ASTM D792
Molding Shrinkage - Flow	1.4 to 2.2	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>1</sup>	3470	MPa	ASTM D638
Tensile Strength (Yield)	53.8	MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	24	%	ASTM D638
Flexural Modulus	2810	МРа	ASTM D790
Flexural Strength	93.1	МРа	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 6.35 mm,			
Injection Molded)	59	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Annealed, 3.18 mm)	72.8	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	71.1 to 82.2	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	277 to 299	°C	
Mold Temperature	82.2 to 104	°C	
NOTE			
1.	Type I, 5.1 mm/min		
2.	Type I, 5.1 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

