

Escorene™ Ultra FL 02020

Ethylene Vinyl Acetate Copolymer Resin

ExxonMobil Chemical

Message:

FL 02020 is mainly designed for high speed/low coating extrusion coating, and is a good coextrusion component that can be matched with other polymers. FL 02020 is an excellent heat sealing material with extremely low sealing temperature and high transparency. Good extrusion coating effect can be obtained at 220°C (428 °F) under processing conditions. Processing temperatures above 240°C (464 °F) may cause resin degradation. FL02020 should be put into the extruder after low density polyethylene with similar or higher melt index. The machine should be thoroughly cleaned with low density polyethylene or suitable detergent before stopping.

General Information			
Additive	heat stabilizer		
Physical	Nominal Value	Unit	Test Method
Vinyl Acetate Content	20.0	wt%	ExxonMobil Method
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	87		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	35.0	MPa	ASTM D638
Tensile Elongation ² (Break)	> 100	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	48.0	°C	ASTM D1525
Legal statement			
本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用有关潜在食品接触应用合规信息(例如:FDA,EU,HPFB),请与埃克森美孚化工客户服务代表联系.			
Extrusion instructions			
Excellent results are obtained in extrusion coating at 220°C (428°F) temperature range. Processing temperatures above 240°C (464°F) may cause resin degradation. FL02020 should be fed into the extruder after LDPE of a similar or higher melt index. Machines should always be purged with LDPE or a suitable cleaning compound before shutdown.			
NOTE			
1.	5.0 mm/min		
2.	500 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT