

QR Resin QR-1000-GF40

Polycarbonate

QTR, Inc.

Message:

Available with UV (V) or Release (R).

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Features	Good Toughness		
Appearance	Colors Available		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.52	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10 to 20	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.20	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	159	MPa	ASTM D638
Flexural Modulus	9650	MPa	ASTM D790
Flexural Strength (Yield)	183	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (23°C)	1200	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	154	°C	
1.8 MPa, Unannealed	146	°C	
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 to 6.0	hr	
Drying Time, Maximum	6.0	hr	
Rear Temperature	293 to 316	°C	
Middle Temperature	304 to 327	°C	
Front Temperature	316 to 338	°C	
Nozzle Temperature	310 to 332	°C	
Processing (Melt) Temp	316 to 338	°C	
Mold Temperature	82.2 to 116	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

