Fluoroplex F 15 - GMF

Polytetrafluoroethylene

UNIFLON

Message:

Fluoroplex F 15-GMF is a polytetrafluoroethylene (PTFE) product, which contains a 15% glass fiber reinforced material. It can be processed by sintering or injection molding and is available in North America or Latin America.

| General Information | | | |
|---------------------------------|---|-------|-----------------|
| Filler / Reinforcement | Glass fiber reinforced material, 15% filler by weight | | |
| Features | Good liquidity | | |
| Processing Method | Sintering | | |
| | Injection molding | | |
| | | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 2.19 - 2.23 | g/cm³ | Internal method |
| Contractility-Sintering | 1.0 - 2.0 | % | Internal method |
| Sintering Temperature - Maximum | 365 | °C | |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore D) | 60 - 63 | | Internal method |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Strength | 18.4 | MPa | Internal method |
| Tensile Elongation (Break) | 180 | % | Internal method |
| Additional Information | Nominal Value | Unit | |
| Code: 010024302 | | | |
| Injection | Nominal Value | Unit | |
| Mold Temperature | 21.0 - 25.0 | °C | |
| Injection Pressure | 44.1 - 53.9 | MPa | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

