

LNP™ LUBRICOMP™ AL003 compound

Acrylonitrile Butadiene Styrene

SABIC Innovative Plastics

Message:

LNP LUBRICOMP* AL003 is a compound based on Acrylonitrile Butadiene Styrene resin containing PTFE. Added features of this material include: Internally Lubricated.
Also known as: LNP* LUBRICOMP* Compound AL-4030
Product reorder name: AL003

General Information			
Additive	PTFE lubricant		
Features	Lubrication		
RoHS Compliance	RoHS compliance		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow: 24 hours	0.60 - 0.80	%	ASTM D955
Transverse flow: 24 hours	0.80 - 1.0	%	ASTM D955
Vertical flow direction: 24 hours	0.80 - 1.0	%	ISO 294-4
Flow direction: 24 hours	0.60 - 0.80	%	ISO 294-4
Water Absorption			
24 hr, 50% RH	0.20	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.31	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2410	MPa	ASTM D638
--	2290	MPa	ISO 527-2/1
Tensile Strength			
Yield	35.9	MPa	ASTM D638
Yield	35.0	MPa	ISO 527-2
Fracture	32.4	MPa	ASTM D638
Fracture	32.0	MPa	ISO 527-2
Tensile Elongation			
Yield	2.3	%	ASTM D638
Yield	2.7	%	ISO 527-2
Fracture	15	%	ASTM D638
Fracture	12	%	ISO 527-2
Flexural Modulus			
--	2060	MPa	ASTM D790
--	2000	MPa	ISO 178
Flexural Strength			

--	62.1	MPa	ASTM D790
--	61.9	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	59	J/m	ASTM D256
23°C ²	5.4	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	200	J/m	ASTM D4812
23°C ³	21	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	11.4	J	ASTM D3763
--	8.23	J	ISO 6603-2
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

