

# YUPLENE® R372Y

Polypropylene Random Copolymer

SK Global Chemical

Message:

Yuplene R372Y is random polypropylene that is made for injection molding. It has high impact strength and excellent transparency. Since it has excellent odor property and dimensional stability, it can be used for food packaging, packaging container, and disposable syringe and various home appliances. Yuplene R372Y complies with FDA regulation 21 CFR 177.1520 for the exposure to food.

General Information			
Features	Food Contact Acceptable		
	Good Dimensional Stability		
	High Impact Resistance		
	Low to No Odor		
Uses	Appliances		
	Containers		
	Food Packaging		
	Medical/Healthcare Applications		
Agency Ratings	FDA 21 CFR 177.1520		
Appearance	Clear/Transparent		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	14	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	85		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	29.4	MPa	ASTM D638
Tensile Elongation (Break)	> 500	%	ASTM D638
Flexural Modulus	1080	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	64	J/m	ASTM D256
Aging	Nominal Value	Unit	Test Method
Accelerated Oven Aging - in Air (150°C)	15.0	day	ASTM D3012
Heat Deflection Temperature	94	°C	ASTM D648
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	135	°C	ASTM D1525
Optical	Nominal Value	Unit	Test Method
Haze	< 10	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

