

Chemlon® MDF35

Polyamide 6

Teknor Apex Company (Chem Polymer)

Message:

MDF35 is a 35% glass fibre reinforced nylon 6 that offers superior mechanical performance coupled with good surface finish. finish and mould release characteristics.

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 35% filler by weight		
Features		Good demoulding performance		
		Excellent appearance		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.41	--	g/cm ³	ISO 1183
Molding Shrinkage ¹	0.70 - 1.2	--	%	Internal method
Water Absorption (Equilibrium, 23°C, 50% RH)	1.9	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	10000	8000	MPa	ISO 527-2
Tensile Stress	180	120	MPa	ISO 527-2
Tensile Strain (Break)	4.0	6.0	%	ISO 527-2
Flexural Modulus	9200	4500	MPa	ISO 178
Flexural Stress	260	140	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	17	37	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	55	--	kJ/m ²	ISO 179/1eU
Notched Izod Impact	14	--	kJ/m ²	ISO 180/A
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	> 200	--	°C	ISO 75-2/B
1.8 MPa, not annealed	> 200	--	°C	ISO 75-2/A
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+15	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+17	1.0E+14	ohms · cm	IEC 60093
Dielectric Strength (3.00 mm)	11	8.0	kV/mm	IEC 60243-1
Relative Permittivity	3.80	4.20		IEC 60250

Comparative Tracking Index	500	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.750 mm, UL listing - Black only)	HB	--		UL 94
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	20		hr	
Rear Temperature	250 - 280		°C	
Middle Temperature	250 - 280		°C	
Front Temperature	250 - 280		°C	
Processing (Melt) Temp	250 - 290		°C	
Mold Temperature	70.0 - 90.0		°C	
Injection Rate	Fast			
Back Pressure	Low			
Screw Speed	Moderate			
Injection instructions				
No drying is necessary unless the material has been exposed to air for longer than three hours. The appearance of splash marks on the surface of mouldings indicates excessive moisture is present.				
NOTE				

1. Mould shrinkage is significantly influenced by many factors including wall thickness, gating, moulding shape and processing conditions. The range values given are determined from specimen bar mouldings of 1.5mm to 4mm wall thickness. They are provided as a guide for comparison purposes only and no guarantee should be inferred from their inclusion. (Specimens measured in the dry state, 24 hours after moulding).

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT