

# NANCAR® 2875

Acrylonitrile Butadiene Rubber

Nantex Industry Co., Ltd.

## Message:

NANCAR® 2875 is a medium acrylonitrile butadiene copolymer with medium oil resistance. It is polymerized at low temperature and contains sufficient antioxidant for normal aging conditions. It has superior processing characteristics, fast curing rate, low mold fouling and superior resilience properties. NANCAR® 2875 is recommended for use in applications requiring improved low temperature properties. It provides excellent extrusions and general processing improvement.

General Information			
Additive	Antioxidant		
Features	Antioxidant		
	Copolymer		
	Fast Cure		
	Good Processability		
	Oil Resistant		
Uses	Low Temperature Applications		
Forms	Pellets		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.970	g/cm <sup>3</sup>	
Mooney Viscosity (ML 1+4, 100°C)	77	MU	ASTM D1646
Acrylonitrile Content - Bound	28.0	%	Internal Method
Solubility - in MEK	100	%	
Stabilizer	Non-staining		
Heat Loss	0.25	%	ASTM D5688
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A <sup>1</sup>	70		
Shore A <sup>2</sup>	69		
Shore A <sup>3</sup>	68		
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
300% Strain <sup>4</sup>	9.51	MPa	
300% Strain <sup>5</sup>	10.4	MPa	
300% Strain <sup>6</sup>	10.7	MPa	
Tensile Strength			ASTM D412
Yield <sup>7</sup>	26.9	MPa	
Yield <sup>8</sup>	28.3	MPa	
Yield <sup>9</sup>	28.5	MPa	

Tensile Elongation			ASTM D412
Break <sup>10</sup>	610	%	
Break <sup>11</sup>	570	%	
Break <sup>12</sup>	540	%	
Tear Strength	61.8	kN/m	ASTM D624
Compression Set <sup>13</sup> (100°C, 70 hr)	53	%	ASTM D395
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air <sup>14</sup> (100°C, 70 hr)	-9.0	%	ASTM D865
Change in Ultimate Elongation in Air <sup>15</sup> (100°C, 70 hr)	-30	%	ASTM D865
Change in Durometer Hardness in Air <sup>16</sup> (Shore A, 100°C, 70 hr)	4.0		ASTM D865
Change in Tensile Strength <sup>17</sup>			ASTM D471
100°C, 70 hr, in ASTM #1 Oil	-7.6	%	
100°C, 70 hr, in ASTM #3 Oil	-39	%	
Change in Ultimate Elongation <sup>18</sup>			ASTM D471
100°C, 70 hr, in ASTM #1 Oil	-18	%	
100°C, 70 hr, in ASTM #3 Oil	-32	%	
Change in Durometer Hardness <sup>19</sup>			ASTM D471
Shore A, 100°C, 70 hr, in ASTM #1 Oil	1.0		
Shore A, 100°C, 70 hr, in ASTM #3 Oil	-9.0		
Change in Volume <sup>20</sup>			ASTM D471
100°C, 70 hr, in ASTM Oil #1	1.7	%	
100°C, 70 hr, in ASTM Oil #3	22	%	
NOTE			
1.	Cured for 60.0 min at 150°C		
2.	Cured for 40.0 min at 150°C		
3.	Cured for 20.0 min at 150°C		
4.	Cured for 20.0 min at 150°C		
5.	Cured for 40.0 min at 150°C		
6.	Cured for 60.0 min at 150°C		
7.	Cured for 60.0 min at 150°C		
8.	Cured for 40.0 min at 150°C		
9.	Cured for 20.0 min at 150°C		
10.	Cured for 20.0 min at 150°C		
11.	Cured for 40.0 min at 150°C		
12.	Cured for 60.0 min at 150°C		
13.	Cured for 60.0 min at 150°C		
14.	Cured for 40.0 min at 150°C		
15.	Cured for 40.0 min at 150°C		
16.	Cured for 40.0 min at 150°C		
17.	Cured for 40.0 min at 150°C		

18.	Cured for 40.0 min at 150°C
19.	Cured for 40.0 min at 150°C
20.	Cured for 40.0 min at 150°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

