# Geon<sup>™</sup> Vinyl Packaging 161J-1

## Rigid Polyvinyl Chloride

### PolyOne Corporation

#### Message:

Geon<sup>™</sup> Vinyl Packaging 161J-1 is a Rigid Polyvinyl Chloride product. It can be processed by blow molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Applications of Geon<sup>™</sup> Vinyl Packaging 161J-1 include bottles and packaging. Characteristics include: High Gloss Impact Resistant

General Information Features **General Purpose High Gloss** High Impact Resistance Uses **Bottles** General Purpose Packaging Appearance Clear/Transparent Forms Pellets Processing Method **Blow Molding** Physical Nominal Value Unit Test Method Specific Gravity ---1.32 g/cm<sup>3</sup> ASTM D792 --0.801 g/cm<sup>3</sup> ASTM D1505 Hardness Nominal Value Unit Test Method Rockwell Hardness (R-Scale) 105 ASTM D785 Durometer Hardness (Shore D) 80 ASTM D2240 Mechanical Nominal Value Unit Test Method Tensile Modulus <sup>1</sup> 2300 MPa ASTM D638 Tensile Strength<sup>2</sup> (Yield) 44.8 MPa ASTM D638 Flexural Modulus 2650 MPa ASTM D790 Flexural Strength 83.4 MPa ASTM D790 Nominal Value Unit Test Method Impact Notched Izod Impact (23°C, 3.18 mm, Injection Molded) 1100 ASTM D256A J/m Thermal Nominal Value Unit Test Method Deflection Temperature Under Load (1.8 °C MPa, Unannealed, 3.18 mm) 69.4 ASTM D648 Optical Nominal Value Unit Test Method Internal Method Transmittance

851 μm, 400 nm	80.5	%
851 μm, 700 nm	86.5	%
Additional Information	Nominal Value	Unit
Blow Molding Temperature	199 to 213	°C
NOTE		
1.	Type I, 5.1 mm/min	
2.	Type I, 51 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

