

Zytel® RS LC2800 NC010

RENEWABLY SOURCED™ POLYAMIDES*

DuPont Performance Polymers

Message:

Plasticized, Renewably Sourced, Polyamide Developed for Extrusion

General Information			
Additive	Heat Stabilizer Plasticizer		
Features	Heat Stabilized Plasticized		
Uses	Film Profiles Sheet		
Forms	Pellets		
Processing Method	Coating Extrusion Film Extrusion Profile Extrusion Sheet Extrusion		
Multi-Point Data	Shear Modulus vs. Temperature (ISO 11403-1) Tensile Modulus vs. Temperature, Dynamic (ISO 11403-1)		
Part Marking Code (ISO 11469)	>PA-P<		
Resin ID (ISO 1043)	PA-P		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	550	MPa	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	16	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature ¹	30.0	°C	ISO 11357-2
Melting Temperature ²	220	°C	ISO 11357-3
NOTE			
1.	10°C/min		
2.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

