

KIBISAN® PN-107 L125

Styrene Acrylonitrile

CHI MEI CORPORATION

Message:

KIBISAN® PN-107 L125 is a Styrene Acrylonitrile (SAN) product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

Flame Rated

RoHS Compliant

General Information			
UL YellowCard	E56070-501316		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.06	g/cm ³	ASTM D792
23°C	1.06	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	5.0	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	44.0	cm ³ /10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale, 6.35 mm)	83		ASTM D785
Ball Indentation Hardness (H 358/30)	155	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			
Yield	52.0	MPa	ISO 527-2/50
Break	52.0	MPa	ISO 527-2/50
3.18 mm ¹	60.8	MPa	ASTM D638
Tensile Elongation			
Break, 3.18 mm ²	5.0	%	ASTM D638
Break	4.0	%	ISO 527-2/50
Flexural Modulus			
6.35 mm ³	3430	MPa	ASTM D790
-- ⁴	2600	MPa	ISO 178
Flexural Strength			
6.35 mm ⁵	88.3	MPa	ASTM D790
-- ⁶	89.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	2.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	18	kJ/m ²	ISO 179
Notched Izod Impact			
23°C, 3.18 mm	18	J/m	ASTM D256

23°C, 6.35 mm	17	J/m	ASTM D256
--	2.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength	15	kJ/m ²	ISO 180/1U
Impact Flexural Test			DIN 53453
Notched	3.00	kJ/m ²	
Unnotched	15.0	kJ/m ²	

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 6.35 mm ⁷	90.0	°C	ASTM D648
1.8 MPa, Unannealed	88.0	°C	ISO 75-2/A
1.8 MPa, Annealed, 6.35 mm ⁸	100	°C	ASTM D648
1.8 MPa, Annealed	99.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	104	°C	ASTM D1525 ⁹
--	105	°C	ISO 306/A50
--	108	°C	ISO 306/A120
--	101	°C	ISO 306/B50
--	103	°C	ISO 306/B120

Flammability	Nominal Value	Test Method
Flame Rating (1.60 mm)	HB	UL 94

NOTE	
1.	6.0 mm/min
2.	6.0 mm/min
3.	2.8 mm/min
4.	2.0 mm/min
5.	2.8 mm/min
6.	2.0 mm/min
7.	120°C/hr
8.	120°C/hr, Annealed at 85°C for 8 hr
9.	Rate A (50°C/h)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT