

VESTOLIT® P 1430 K 70 Ultra

Polyvinyl Chloride Homopolymer

VESTOLIT GmbH & Co. KG

Message:

VESTOLIT P 1430 K 70 Ultra is a paste-forming homopolymer which is suitable for producing low viscosity pastes with almost Newtonian flow. VESTOLIT P 1430 K 70 Ultra is particularly suited to the production of compact pastes.

| General Information | | | |
|--------------------------------------|-----------------------------|-------------------|-------------|
| Features | Good Flow | | |
| | Good Thermal Stability | | |
| | High Clarity | | |
| | High Gloss | | |
| | Homopolymer | | |
| | Low Viscosity | | |
| Uses | Coating Applications | | |
| | Fabric Coatings | | |
| | Film | | |
| | Flooring Maintenance/Repair | | |
| Appearance | Clear/Transparent | | |
| Forms | Paste | | |
| Processing Method | Coating | | |
| | Dip Coating | | |
| | Film Extrusion | | |
| | Spraying | | |
| Physical | Nominal Value | Unit | Test Method |
| Apparent Density | 0.35 | g/cm ³ | ISO 60 |
| K-Value | 70.0 | | ISO 1628-2 |
| Viscosity Number (Reduced Viscosity) | 125.0 | ml/g | ISO 1628 |
| pH | 6.0 | | ISO 1264 |
| Sieve Analysis ¹ | < 1.0 | % | ISO 1624 |
| Viscosity - Paste | | | |
| -- ² | 2.50 | Pa · s | |
| -- ³ | 3.00 | Pa · s | |
| Water Content ⁴ | < 0.30 | % | DIN 53715 |
| NOTE | | | |
| 1. | 0.063 mm sieve | | |
| 2. | 1.5 s/1 | | |

| | |
|----|-------------|
| 3. | 45 s/1 |
| 4. | Karl Fisher |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

