Jampilen EP440L

Polypropylene Copolymer

Jam Polypropylene Company

Message:

General Information

Jampilen EP440L is a medium flow heterophasic polypropylene copolymer with improved mechanical properties balance. The product features high stiffness and outstanding impact strength at low temperatures and is specifically designed for injection molding applications. In comparison with conventional copolymers with the same MFR and same rigidity, Jampilen EP440L, exhibits 35 % higher toughness. Jampilen EP440L is suitable for a wide range of applications in the packaging, automotive and consumer goods industries. Typical applications include luggage, paint pails, buckets, containers, crates, batteries and large toys.

General information				
Features	Copolymer			
	High Impact Resistance			
	High Stiffness			
	Low Temperature Impact Resistance			
	Medium Flow			
Uses	Automotive Applications			
	Batteries			
	Consumer Applications			
	Containers			
	Crates			
	Luggage			
	Packaging			
	Toys			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Density	0.900	g/cm³	ASTM D1505	
Melt Mass-Flow Rate (MFR) (230°C/2.16		40.		
kg)	6.0	g/10 min	ASTM D1238	
Hardness	Nominal Value	Unit	Test Method	
Shore Hardness (Shore D)	68		ISO 868	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Yield)	26.0	MPa	ASTM D638	
Tensile Elongation (Yield)	9.0	%	ASTM D638	
Flexural Modulus	1400	MPa	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact			ASTM D256	
-20°C	70	J/m		
23°C	170	J/m		
Thermal	Nominal Value	Unit	Test Method	

Deflection Temperature Under Load (0.4	1 5		
MPa, Unannealed)	95.0	°C	ASTM D648
Vicat Softening Temperature	152	°C	ASTM D1525 ¹
Accelerated Oven Ageing (150°C)	360	hr	ASTM D3012
NOTE			
1.	Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

