

Multilon® T-2760B

Polycarbonate + ABS

TEIJIN LIMITED

Message:

PC/ABS polymer alloy, T-2700 series, Automotive series

General Information			
Features	Gloss, low		
	Impact resistance, good		
	High liquidity		
Uses	Car interior parts		
	Automotive exterior parts		
	Car dashboard		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.11	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (250°C/5.0 kg)	14.0	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal method
Transverse flow: 4.00mm	0.50 - 0.70	%	Internal method
Flow: 4.00mm	0.50 - 0.70	%	Internal method
Water Absorption (23°C, 24 hr)	0.20	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Pencil Hardness	2B to B		JIS K5600
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2050	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield, 23°C	47.0	MPa	ISO 527-2/50
Fracture, 23°C	40.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	3.0	%	ISO 527-2/50
Fracture, 23°C	80	%	ISO 527-2/50
Flexural Modulus ¹ (23°C)	2100	MPa	ISO 178
Flexural Stress ² (23°C)	70.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	30	kJ/m ²	ISO 179

23°C	75	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	113	°C	ISO 75-2/B
1.8 MPa, not annealed	95.0	°C	ISO 75-2/A
Vicat Softening Temperature	112	°C	ISO 306/B50
Linear thermal expansion coefficient			ISO 11359-2
Flow	8.0E-5	cm/cm/°C	ISO 11359-2
Lateral	8.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT