

Andur 9000 AS

Polyurethane (TDI)
Anderson Development Company

Message:

Andur 9000-AS is a two-component liquid urethane system which can be processed at room temperature to yield an elastomer with a hardness of 90 to 92 Shore A.
Andur 9000-AS is recommended where ease of processing is desired.

General Information			
Forms	Liquid		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm ³	ASTM D792
Thermoset	Nominal Value	Unit	Test Method
Thermoset Mix Viscosity (25°C)	500	cP	ASTM D2393
Additional Information			

Specific Gravity, ASTM D792, 77°F: 1.11 g/ml

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

