

TAROLOX 111 G6 Y0

Polyethylene Terephthalate

Taro Plast S.p.A.

Message:

PET medium viscosity 30% glass fibres reinforced, halogen free flame retardant UL94 V0, heat stabilized, good flow, good mechanical, thermal and electrical properties, low moisture absorption, good dimensional stability.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Flame Retardant		
	Heat Stabilizer		
Features	Flame Retardant		
	Good Dimensional Stability		
	Good Flow		
	Halogen Free		
	Heat Stabilized		
	Low Moisture Absorption		
	Medium Viscosity		
Uses	Electrical/Electronic Applications		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.59	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow	0.50 to 0.70	%	
Flow	0.20 to 0.30	%	
Water Absorption (23°C, 24 hr)	0.050	%	ISO 62
Granule Humidity ¹	< 0.030	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	12300	MPa	ISO 527-2/1
Tensile Stress (Break)	105	MPa	ISO 527-2/50
Tensile Strain (Break)	1.6	%	ISO 527-2/50
Flexural Modulus ²	11000	MPa	ISO 178
Flexural Stress ³	150	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	8.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	42	kJ/m ²	ISO 179/1eU
Notched Izod Impact			ASTM D256

-20°C	70	J/m	
23°C	85	J/m	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁴ (1.8 MPa, Unannealed)	235	°C	ISO 75-2/A
Continuous Use Temperature	150	°C	IEC 60216
Vicat Softening Temperature	237	°C	ISO 306/B50
Ball Pressure Test (245°C)	Pass		IEC 60695-10-2
Melting Temperature	256	°C	ISO 11357-3
CLTE - Flow (-30 to 30°C)	2.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	V-0		
1.60 mm	V-0		
3.20 mm	V-0		
Glow Wire Flammability Index (1.00 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (1.00 mm)	775	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	110 to 130	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	260 to 290	°C	
Mold Temperature	100 to 130	°C	
Injection Rate	Moderate-Fast		
NOTE			
1.	TARO 002		
2.	1.0 mm/min		
3.	1.0 mm/min		
4.	120°C/hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT