# **NuSil R-3900**

#### Silicone

#### **NuSil Technology**

#### Message:

The Aircraft Industry has used silicone adhesives and coatings for over five decades. Silicone's ability to maintain its elasticity and low modulus over a broad temperature range provides excellent utility in extreme environments. Recent advances in material technology provide more opportunities for the Aircraft engineer in choosing the best material for an intended application. Examples of NuSil's capabilities in custom silicones for Aircraft are demonstrated in the following sections.

**Fuel Resistance** 

Static Dissipation and Electrically Conductive Silicones

Ice-Phobic Coatings General Purpose: Coatings

Comment: Cure: 8 h/25°C: 45 m/75°C: 135 m/150°C, Dispersion Coating, 20% Solids

General Information			
Features	Electrically Conductive		
	Fuel Resistant		
Uses	Aircraft Applications		
	Coating Applications		
	Electrical/Electronic Applications		
Physical	Nominal Value	Unit	
Solids Content	20	%	
Cure System	Platinum		
Operating Temperature	-50 to 200	°C	
Thermoset	Nominal Value	Unit	
Thermoset Components			
Part A	Mix Ratio by Weight: 1.0		
Part B	Mix Ratio by Weight: 1.0		
Uncured Properties	Nominal Value	Unit	
Color	Translucent		
Viscosity	1.9	Pa·s	
Curing Time			
75°C	0.75	hr	
25°C	8.0	hr	
Cured Properties	Nominal Value	Unit	
Shore Hardness (Shore A)	50		
Tensile Strength	8.27	MPa	
Tensile Elongation at Break	900	%	
Tear Strength	48.2	kN/m	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2