

VICTREX® HT™ P45

Polyether Ketone

Victrex plc

Message:

High performance thermoplastic material, unreinforced PolyEtherKetone (PEK), semi crystalline, coarse powder for extrusion compounding, low flow, FDA food contact compliant, colour natural.

General Information			
Features	Food Contact Acceptable		
	Low Flow		
	Semi Crystalline		
Agency Ratings	FDA Food Contact, Unspecified Rating		
Appearance	Natural Color		
Forms	Powder		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density ¹	1.30	g/cm³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	3500	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	100	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	15	%	ISO 527-2
Flexural Modulus (23°C)	4000	MPa	ISO 178
Flexural Stress (23°C)	180	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	6.5	kJ/m²	ISO 180/A
Unnotched Izod Impact Strength (23°C)	No Break		ISO 180
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	152	°C	ISO 11357-2
Melting Temperature	373	°C	ISO 11357-3
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (400°C)	350	Pa·s	ISO 11443
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

