# SABIC® LDPE PCG01

## Low Density Polyethylene

## Saudi Basic Industries Corporation (SABIC)

#### Message:

SABIC® LDPE grades for healthcare applications are produced under controlled conditions resulting in high product quality, consistency and a high level of purity.

SABIC<sup>®</sup> LDPE PCG01 is an additive-free grade produced using SABIC's proprietary high pressure Clean Tubular Reactor (CTR<sup>®</sup>) which typically ensures grades with high purity. It is typically used for semi-rigid containers obtained by Blow Fill Seal (BFS) process and medical films. Compliance to Regulations

SABIC® LDPE PCG01 complies with the relevant monographs of the European Pharmacopoeia (EP) and the United States Pharmacopoeia (USPVI).

General Information			
Features	Additive Free		
	High Purity		
	Low Density		
Uses	Containers		
	Film		
	Medical/Healthcare Applications		
Agency Ratings	EP Unspecified Rating		
	USP Class VI		
Physical	Nominal Value	Unit	Test Method
Density	0.925	g/cm³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (190°C/2.16			
kg)	0.75	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction	0.90		ASTM D1894
Films	Nominal Value	Unit	Test Method
Tensile Modulus			ISO 527-3
MD	200	MPa	
TD	200	MPa	
Tensile Stress			ISO 527-3
MD : Yield	12.0	MPa	
TD : Yield	12.0	MPa	
MD : Break	25.0	MPa	
TD : Break	20.0	MPa	
Tensile Elongation			ISO 527-3
MD : Break	> 200	%	
TD : Break	> 500	%	
Impact	Nominal Value	Unit	Test Method

Impact Strength	150	J/cm	ASTM D4272
Blocking	20	g	Internal Method
Re-blocking	< 5.0	g	Internal Method
Tear Strength			ISO 6383-2
MD	45.0	kN/m	
TD	45.0	kN/m	
	-5.0	KIN/III	
Thermal	Nominal Value	Unit	Test Method
		·	Test Method ISO 306/A
Thermal	Nominal Value	Unit	
Thermal Vicat Softening Temperature	Nominal Value 98.0	Unit °C	ISO 306/A
Thermal   Vicat Softening Temperature   Melting Temperature (DSC)	Nominal Value 98.0 113	Unit °C °C	ISO 306/A DIN 53765

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

