

K-vinyl FRLS 98

Flexible Polyvinyl Chloride

Technovinyl Polymers India Ltd.

Message:

K-vinyl FRLS 98 is a Flexible Polyvinyl Chloride material. It is available in Africa & Middle East. Primary attribute of K-vinyl FRLS 98: RoHS Compliant.
Typical application of K-vinyl FRLS 98: Wire & Cable

General Information			
Features	Low (to None) Lead Content		
Uses	Wire & Cable Applications		
RoHS Compliance	RoHS Compliant		
Hardness	Nominal Value		Test Method
Durometer Hardness (Shore A)	94 to 98		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	> 13.0	MPa	ASTM D412
Tensile Elongation (Break)	> 200	%	ASTM D412
Thermal	Nominal Value	Unit	
Temperature Index	250	%	
Smoke Density	< 55	%	ASTM D2839
Emission - HCL	< 20	%	IEC 754-1
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	> 30	%	ASTM D2863

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT