

BJB Polyurethane F-85 A/B

Polyurethane Thermoset Elastomer

BJB Enterprises, Inc.

Message:

The F-85 A/B system is a prodution oriented fast gel and fast de-mold material. It features a working time which allows time to mix, vacuum de-gas, and pour air-free parts. F-85 A/B can be demolded in as little as one hour depending on part size and configuration.

General Information			
Features	Rapid solidification crystal point		
Uses	Sealing device		
	Car anti-collision bar		
	Mold/Mold/Tool		
Appearance	Opacity		
	Light yellow		
Forms	Liquid		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.08	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.30	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	85		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	17.2	MPa	ASTM D412
Tensile Elongation (Break)	280	%	ASTM D412
Tear Strength	31.5	kN/m	ASTM D624
Thermoset	Nominal Value	Unit	Test Method
Shelf Life (25°C)	26	wk	
Thermoset Mix Viscosity (24°C)	2000	cP	ASTM D2393
Demold Time (25°C)	60 - 120	min	
Post Cure Time (66°C)	4.0	hr	
Additional Information			

The value listed a Mold Shrink, linear-flow was tested in accordance with ASTM D-2566Mix ratio by weight: 60/100Mix ratio by volume: 57/100Work time, 100 g, 77°F: 4 minGel time: 5 min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

