

Hostaform® C 27021 XAP C

Acetal (POM) Copolymer

Celanese Corporation

Message:

POM copolymer

Easy flow injection molding grade with very low emissions and migrations; designed for consumer packaging

Emission according to VDA 275 <2 mg/kg (natural grades)

Monomers and additives are listed in EU-Regulation (EU) 10/2011

FDA compliant according to 21 CFR 177.2470

FDA = Food and Drug Administration (USA)

General Information			
Features	Low volatilization		
	Good liquidity		
	Mobility Low to None		
Uses	Packaging		
Agency Ratings	FDA 21 CFR 177.2470		
	Europe 10/1/2011 12:00:00 AM		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	24.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Transverse flow	1.8	%	ISO 294-4
Flow	1.9	%	ISO 294-4
Water Absorption (Saturation, 23°C)	0.65	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2900	MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	65.0	MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	7.5	%	ISO 527-2/1A/50
Nominal Tensile Strain at Break	17	%	ISO 527-2/1A/50
Tensile Creep Modulus			ISO 899-1
1 hr	2500	MPa	ISO 899-1
1000 hr	1300	MPa	ISO 899-1
Flexural Modulus (23°C)	2800	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	5.5	kJ/m ²	ISO 179/1eA

23°C	5.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	120	kJ/m ²	ISO 179/1eU
23°C	120	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	106	°C	ISO 75-2/A
Melting Temperature ¹	166	°C	ISO 11357-3
CLTE - Flow	1.1E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+14	ohms · cm	IEC 60093
Dielectric Strength	35	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	4.00		IEC 60250
1 MHz	4.00		IEC 60250
Dissipation Factor			IEC 60250
100 Hz	2.5E-3		IEC 60250
1 MHz	5.0E-3		IEC 60250
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.5 mm	HB		UL 94
3.0 mm	HB		UL 94
Fill Analysis	Nominal Value	Unit	Test Method
Melt Density	1.20	g/cm ³	Internal method
Melt Specific Heat	2210	J/kg/°C	Internal method
Melt Thermal Conductivity	0.16	W/m/K	Internal method
Ejection Temperature	140	°C	Internal method
Injection	Nominal Value	Unit	
Drying Temperature	120 - 140	°C	
Drying Time	3.0 - 4.0	hr	
Suggested Max Moisture	0.15	%	
Hopper Temperature	20 - 30	°C	
Rear Temperature	170 - 180	°C	
Middle Temperature	180 - 190	°C	
Front Temperature	190 - 200	°C	
Nozzle Temperature	190 - 210	°C	
Processing (Melt) Temp	190 - 210	°C	
Mold Temperature	80 - 120	°C	
Injection Pressure	60.0 - 120	MPa	
Injection Rate	Slow-Moderate		

Holding Pressure	60.0 - 120	MPa
Back Pressure	0.00 - 4.00	MPa
Screw L/D Ratio	15.0:1.0 to 25.0:1.0	
Injection instructions		
Feed Temperature: 60 to 80°CZone 4 Temperature: 190 to 210°CManifold Temperature: 190 to 210°C		
NOTE		
1.	10°C/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT