

Premier PR350M

Polypropylene Random Copolymer

Premier Polymers, LLC.

Message:

Premier PR350M is a high melt flow random polypropylene suitable for extrusion and thermoforming applications requiring clarity and processability. Meets all requirements of the U. S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact.

General Information			
Features	Food Contact Acceptable		
	Good Processability		
	High Clarity		
	High Flow		
Agency Ratings	FDA 21 CFR 177.1520		
Processing Method	Extrusion		
	Thermoforming		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	35	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	29.0	MPa	ASTM D638
Tensile Elongation ² (Yield)	13	%	ASTM D638
Flexural Modulus - 1% Secant ³	1030	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	270	J/m	ASTM D256
Optical	Nominal Value	Unit	Test Method
Haze	12	%	FTTC 5606
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

