

Ecomass® 4703ZC57

Thermoplastic Polyurethane Elastomer

Ecomass Technologies

Message:

Ecomass® 4703ZC57 is a Thermoplastic Polyurethane Elastomer material filled with stainless steel powder. It is available in North America for injection molding.

Important attributes of Ecomass® 4703ZC57 are:

Good Toughness

Non-Toxic

General Information			
Filler / Reinforcement	Stainless Steel Powder		
Features	Non-Toxic		
	Ultra High Toughness		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.29	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.60 to 0.90	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	552	MPa	ASTM D638
Tensile Strength	23.0	MPa	ASTM D638
Tensile Elongation (Break)	800	%	ASTM D638
Flexural Modulus	86.9	MPa	ASTM D790
Flexural Strength	40.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	280	J/m	ASTM D256
Injection	Nominal Value	Unit	
Drying Temperature	71.1 to 93.3	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	204 to 221	°C	
Mold Temperature	10.0 to 26.7	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

