

GXL 10004

Thermoplastic Polyolefin Elastomer

S&E; Specialty Polymers, LLC

Message:

ATP-K-29 (wet electricals) approved

General Information			
Features	Halogen-free		
	Flame retardancy		
Uses	Wire and cable applications		
	Insulating material		
Appearance	Available colors		
	Natural color		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.43	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 3 sec)	90		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	12.8	MPa	ASTM D412
Tensile Elongation (Break)	350	%	ASTM D412
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -30.0	°C	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Dielectric Constant	3.30		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	32	%	ASTM D2863
Additional Information			
Suggested Stock Temperature: 210-230°FTemperature Rating: 105°C			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

