

Huaфон JF-W-AH6050B

Polyurethane
Huaфон Group Co., Ltd.

Message:

Hydrolysis Resistance and High Peeling Strength Type
Characteristics
Mid soft type, high peeling strength, 24 hours hydrolysis resistance, good smoothness, good film property, good film property, suit for high density technology.
Applications
Shoes

General Information		
Features	Good Adhesion	
	Hydrolysis Resistant	
	Soft	
Uses	Footwear	
Additional Information	Nominal Value	Unit
Solvents	DMF	
Uncured Properties	Nominal Value	Unit
Solids Content	34 to 36	%
Viscosity (25°C)	200 to 260	Pa·s
Cured Properties	Nominal Value	Unit
Tensile Modulus (100% Secant)	4.50 to 5.50	MPa
Tensile Strength	> 45.0	MPa
Tensile Elongation at Break	> 550	%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT