# WEVO-CHEMIE Polyurethanes PU 570/300

### Polyurethane

#### WEVO-CHEMIE GmbH

#### Message:

WEVO-CHEMIE Polyurethanes PU 570/300 is a Polyurethane material. It is available in Europe or North America for casting. Primary attribute of WEVO-CHEMIE Polyurethanes PU 570/300: Flame Rated.

Typical applications include:

Automotive

Electrical/Electronic Applications

| General Information                              |                                    |       |             |  |
|--|------------------------------------|-------|-------------|--|
| Features   | General Purpose                    |       |             |  |
| Uses   | Automotive Applications            |       |             |  |
|  | Electrical/Electronic Applications |       |             |  |
| Forms  | Liquid                             |       |             |  |
| Processing Method                                | Casting                            |       |             |  |
| Physical   | Nominal Value                      | Unit  |             |  |
| Water Absorption <sup>1</sup> (Saturation, 23°C) | 0.40                               | %     |             |  |
| Thermal  | Nominal Value                      | Unit  | Test Method |  |
| Glass Transition Temperature                     | 8.00                               | °C    | TMA         |  |
| Thermal Conductivity                             | 0.46                               | W/m/K | ISO 22007-2 |  |
| Flammability                                     | Nominal Value                      |       | Test Method |  |
| Flame Rating                                     | НВ                                 |       | UL 94       |  |
| Thermoset  | Nominal Value                      | Unit  | Test Method |  |
| Thermoset Components                             |                                    |       |             |  |
| Hardener   | Mix Ratio by Weight: 20            |       |             |  |
| Resin  | Mix Ratio by Weight: 100           |       |             |  |
| Pot Life (22°C)                                  | 2.0 to 50                          | min   |             |  |
| Thermoset Mix Viscosity <sup>2</sup> (22°C)      | 1500 to 2000                       | сР    |             |  |
| Additional Information                           | Nominal Value                      | Unit  | Test Method |  |
| Operating Temperature                            | -25 to 130                         | °C    |             |  |
| Uncured Properties                               | Nominal Value                      | Unit  | Test Method |  |
| Density  |                                    |       |             |  |
| 22°C <sup>3</sup>                                | 1.20 to 1.24                       | g/cm³ |             |  |
| 22°C <sup>4</sup>                                | 1.56 to 1.59                       | g/cm³ |             |  |
| Cured Properties                                 | Nominal Value                      | Unit  | Test Method |  |
| Shore Hardness (Shore D)                         | 65 to 70                           |       | ISO 868     |  |
| Tensile Strength                                 | 6.00                               | МРа   | ISO 527     |  |
| Tensile Elongation at Break                      | 60                                 | %     | ISO 527     |  |
| Electric Strength                                | 28                                 | kV/mm | IEC 60243   |  |

| Relative Permittivity (50 Hz, 23°C) | 5.60                  |         | IEC 60250 |
|-------------------------------------|-----------------------|---------|-----------|
| Volume Resistivity                  | 1.0E+14               | ohms·cm | IEC 60093 |
| NOTE                                |                       |         |           |
| 1.                                  | 30 Days               |         |           |
| 2.                                  | Rotational viscometer |         |           |
| 3.                                  | Hardener              |         |           |
| 4.                                  | Resin                 |         |           |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

