

# KEP® 901

Ethylene Propylene Diene Terpolymer

Kumho Polychem Co., Ltd.

## Message:

### Features:

High mooney viscosity & 100PHR oil extended, suitable for low hardness compound

### Applications:

Window seals, moldings in general, low hardness compounds, damping parts, TPV

General Information		
Features	High Viscosity	
	Low Hardness	
Uses	Seals	
	Windows & Doors	
Forms	Bale	
Processing Method	Injection Molding	
Physical	Nominal Value	Unit
Mooney Viscosity (ML 1+8, 125°C)	50	MU
Ethylene Content	70.0	wt%
Ethylidene Norbornene (ENB) Content	4.8	wt%
Oil Type (Unspecified Oil)	100.0	phr

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT