

Sumikon® FM-PF370

Polyamide 6

Sumitomo Bakelite Co., Ltd.

Message:

This molding compound can be used as a substitute for metal parts which require force of inertia

General Information			
UL YellowCard	E41429-232806		
Filler / Reinforcement	Organic filler		
Uses	Metal substitution		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	3.69	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.40	%	ASTM D955
Transverse flow	0.50	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.020	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	70.0	MPa	ASTM D638
Tensile Elongation (Yield)	0.30	%	ASTM D638
Flexural Modulus	21000	MPa	ASTM D790
Flexural Strength (Yield)	108	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	39	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	178	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+6	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	100	°C	
Drying Time	3.0	hr	
Mold Temperature	80.0 - 120	°C	
Injection instructions			

Cylinder temperature: 270 to 320°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

