Lucofin® 1461

Polyolefin

Lucobit AG

Message:

Product description

Lucofin is a coloured, highly stabilized, bitumen-free TPO raw material based on polyolefins. The granules are available in the following standard colour: white

Product properties

Lucofin products display excellent tear resistance, flexibility, and weathering resistance. Lucofin exhibits good toughness, superior biaxial stretchability, and flexibility even at low temperatures. It is insensitive to stress cracking and notch effects. Special stabilization provides good resistance to heat ageing and UV radiation. Lucofin is thus to a large extent resistant to weathering and ageing.

Product advantages

easy processing on standard processing equipment wide colour range easy to weld (hot air/ hot air wedge welding) good mechanical properties flexibility ageing resistant compatible with polyolefins and bitumen according to DIN 16726 environmentally sound long-term experience Applications Coloured Lucofin products are mainly used in construction, for ins

Coloured Lucofin products are mainly used in construction, for instance, for TPO/FPO roofing and swimming pool membranes, profiles for the construction industry and as well as waterstops. Lucofin membranes and profiles can be welded safely and durably. Furthermore, Lucofin is suitable for the production of injection moulded parts in the building sector. In most cases it is necessary to choose the same raw material for parts, profiles and membranes due to the requirement of same colour and stabilization.

Processing

Lucofin products are suited for standard processing equipment used for thermoplastics. We recommend the following processing temperatures as standard values for extrusion.

Profiles: approx. 150° - 180 °C

Membranes/ flat-sheet composites: approx. 160° - 230 °C

Coatings: approx. 160° - 240 °C

For injection moulding Lucofin compounds are processed at melt temperatures ranging from 160° - 220 °C and mould temperatures from 10° - 40 °C. Packaging

Granules: 25 kilo bags, other packaging upon request.

Root resistance

Lucofin roofing and sealing membranes are resistant to penetration by roots according to DIN 16726 and FLL, and root resistant.

Fire protection

Lucofin is categorized as building material class B2.

Chemical resistance

Lucofin is resistant to water and aqueous solutions, salt as well as to dilute acids and bases. When exposed to aliphatic, aromatic and halogen substituted hydrocarbons, Lucofin may swell or dissolve to a certain extent. Lucofin can be supplied as an algicide effective version upon request.

General	Information	

Features

Environmentally Sound Good Chemical Resistance Good Colorability Good Flexibility Good Heat Aging Resistance Good Processability Good Stability Good Stretchability

	Good Tear Strength			
	Good Toughness			
	Good UV Resistance			
	Good Weather Resistance			
	Low Temperature Flexibility			
	Weldable			
Uses	Membranes			
	Profiles			
	Swimming Pools			
Appearance	Light Blue			
Forms	Granules			
Processing Method	Extrusion			
	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Density (23°C)	0.990	g/cm³	ISO 1183	
Melt Mass-Flow Rate (MFR) (190°C/2.16				
kg)	9.0	g/10 min	ISO 1133	
Hardness	Nominal Value	Unit	Test Method	
Shore Hardness (Shore A, 23°C)	95		ISO 868	
Additional Information	Nominal Value	Unit	Test Method	
Low Temperature Flexural Test	< -45	°C	DIN 53361	
Injection	Nominal Value	Unit		
Processing (Melt) Temp	160 to 220	°C		
Mold Temperature	10.0 to 40.0	°C		
Extrusion	Nominal Value	Unit		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

°C

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

150 to 180

Tel: +86 21 5895 8519

Melt Temperature

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

