Aaroprene® ATPR 2040

Styrene Ethylene Butylene Styrene Block Copolymer

Aaron Industries Corp.

Message:

FEATURES: A black thermoplastic SEBS rubber compound specifically designed for the injection molding of industrial gaskets.

General Information			
Uses	Gaskets		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.03	g/cm³	ASTM D792
Apparent Density	0.56	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR)	15	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	40		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.24	MPa	ASTM D412
Flexural Modulus	2.76	MPa	ASTM D412
Taber Abrasion Resistance	290	mg	ASTM D1044
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	6.21	MPa	ASTM D412
Tensile Elongation (Break)	800	%	ASTM D412

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

