

AFFINITY™ GA 1900

Polyolefin Plastomer
The Dow Chemical Company

Message:

Ultra high clarity, low density, low viscosity polyolefin
Excellent thermal stability
Low Tg (Excellent low temperature properties)
Excellent flexibility
Non corrosive
Excellent color and odor
Excellent compatibility with a wide range of polymers
Low crystallinity (can be heavily filled)
Low density (better mileage)
Excellent adhesion to diverse substrates when formulated
Complies with:
U.S. FDA FCN 424
Consult the regulations for complete details.
AFFINITY* GA 1900 Polyolefin Plastomer (POP) is produced via INSITE* Technology from Dow Plastics. This product can be used in applications such as polymer modification (i.e. flow enhancement and property enhancement), masterbatch/additive carrier, and hot melt adhesives.

General Information			
Agency Ratings	FDA FCN 424		
Forms	Pellets		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.870	g/cm ³	ASTM D792
Gardner Color	< 2.00		ASTM D6290
Volatile Matter ¹	< 0.15	%	ASTM D3030
Brookfield Viscosity (177°C)	8.20	Pa · s	ASTM D1084
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	1.55	MPa	ASTM D638
Tensile Elongation (Break)	110	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-57.8	°C	Internal Method
Melting Temperature (DSC)	67.8	°C	Internal Method
NOTE			

1. Modified for polyolefins. Change the temperature used to 100°C +/-3 and the amount of sample to 20 grams.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

